

**What is claimed is:**

1. A functional fiber sheet comprising synthetic fiber, one face or both faces thereof being coated with a physically vapor-deposited film comprising metallic oxides, wherein said  
5 metallic oxides comprise a mixture of ordinary oxides as a main component and a small amount of oxides having a lower valence than the ordinary oxides as a secondary component.
2. The functional fiber sheet as set forth in Claim 1 wherein the amount of lower  
10 valence oxides to the total amount of metallic oxides is 0.1 to 20 wt % and wherein the thickness of said physically vapor-deposited film is 5 to 500 nm.
3. The functional fiber sheet described in Claims 1 or 2 wherein said metallic oxide  
is titanium oxide, its ordinary oxide being a tetravalent oxide and wherein said lower valence  
oxides are divalent or trivalent oxides.  
15
4. A method for manufacturing a functional fiber sheet comprising the steps of:  
forming a physically vapor-deposited film of metallic oxides on a fiber sheet  
through a physical vapor deposition process;  
forming ordinary oxides as a main component of the metallic oxides of the  
20 physically vapor-deposited film by increasing the amount of oxygen to be supplied during the  
physical vapor deposition process; and

forming a small amount of oxides having a lower valence than the ordinary oxides as a secondary component of the metallic oxides by lowering the amount of oxygen to be supplied to the physical vapor deposition process.

5            5. The functional fiber sheet as set forth in Claim 1 wherein the synthetic fiber comprises synthetic fiber used in usual knit and woven use.

6. The functional fiber sheet as set forth in Claim 1 wherein the synthetic fiber comprises polyester fiber, nylon fiber, acrylic fiber or polyimide fiber.

10